



Laserguard AG

Product Code: 2343010
Revised Date: 10/28/2015

Laserguard AG (Tarnish & Corrosion Inhibitor/Silver & Silver Electroplates)

Laserguard AG is a solvent-free, anti-tarnish process for silver and silver electroplates. This process provides an extremely thin, non-hazardous and chemically stable protective layer which prevents sulfide formation. The non-poisonous attribute makes this process safe for flatware and hollowware as well as for other decorative applications including jewelry and ornaments. The surface exhibits negligible electrical resistance and is readily soldered.

OPERATING CONDITIONS

Concentration: 4.2% to 7.8% by volume, **Laserguard AG** in water.
Temperature: 104F-120F (40C-45C)
Immersion time: 1 to 5 minutes
Equipment: Tanks: Stainless Steel,
Polypropylene, PVC, PVDC,
or Polyethylene.
Heater: PTFE coated

OPERATION OF LASERGUARD AG

- Immerse clean and active silver or silver electroplated components in the solution for the required temperature and time.
- Rinse with DI water for 1-3 minutes.
- Dry.

NOTE: Maintain Laserguard AG concentrate above 25C (77F). If solidification occurs, heat container of Laserguard AG to 48C (120F) in tap water.

WASTE TREATMENT

Contact local authorities for guidelines for disposal of waste Laserguard AG and rinse waters.



Better Chemistry. **Better Business.**

Laserguard AG

Product Code: 2343010
Revised Date: 10/28/2015

WARRANTY

THE QUALITY OF THIS PRODUCT IS GUARANTEED ON SHIPMENT FROM OUR PLANT. IF THE USE RECOMMENDATIONS ARE FOLLOWED, DESIRED RESULTS WILL BE OBTAINED. SINCE THE USE OF OUR PRODUCTS IS BEYOND OUR CONTROL, NO GUARANTEE EXPRESSED OR IMPLIED IS MADE AS TO THE EFFECTS OF SUCH USE, OR THE RESULTS TO BE OBTAINED.